

TDS/SPECIFICATION SHEET

ANTIBLOCKMB: HPABF106

Product description

The MB HPABF106 contains talc , recommended for providing antilock properties to LLDPE film and to facilitate the opening of bags in PE. The granular shape of this MB, being very similar to that of the polyolefin resin in terms of size and density, allows an easy mixing/dispersion with the raw materials.

Specifications (Reported on CoA)

Content TALC	38-42%	M ABF

Additional Typical Values

Appearance	Whitish Granules	M001
Bulk Density	0.57-0.64	M003

Recommendations of use

Addition levels of MB HPABF106 depend on various factors such as thickness of the article, expected service life, presence of fillers and other additives and commonly range from 1.0-2.5%. Natural silica is used in cases where excellent optical properties are required. Contact us for your specific recommendation needs.

Packaging

MB HPABF106 is supplied in 25 kg plastic bags on1000 kg or 1375 kg wooden pallets.

Storage Conditions

It is recommended to avoid the exposure of MB HPABF106 to sunlight and high temperatures for longer times as this may impair the quality of the MB. Storage lifetime is 1 year.

Contact

Address: 19 Rue du Mercure, ZI Ben Arous

2013 Ben Arous - Tunisia. Tel: +216 71 383 675 Fax: +216 71 383 716

Email: commercial@hosta-polymers.com

Ed. 01 04/06/2015