

TDS/SPECIFICATION SHEET

ANTIBLOCKMB: HPSABF103

Product description

The MB HPSABF103 contains erucamide and natural silica, recommended for providing antiblock properties to PE films and to reduce the coefficient of friction between two PE films. The granular shape of this MB, being very similar to that of the polyolefin resin in terms of size and density, allows an easy mixing/dispersion with the raw materials.

Specifications (Reported on CoA)

Content natural SILICA	13.5-15.5%	M SABF
Content ERUCAMIDE	3.5-4.5%	M SABF

Additional Typical Values

Appearance	Milky Opaque Granules	M001
Bulk Density	0.57-0.65	M003

Recommendations of use

Addition levels of MB HPSABF103depend on various factors such as thickness of the article, expected service life, presence of fillers and other additives and commonly range from1-3%. It can also be used with other polyolefins. Not to be used in cling film applications containing Polybutene. Contact us for your specific recommendation needs.

Packaging

MB HPSABF103 is supplied in 25 kg plastic bags on 1000 kg or 1375 kg wooden pallets.

Storage Conditions

It is recommended to avoid the exposure of MB HPSABF103to sunlight and high temperatures for longer times as this may impair the quality of the MB. Storage lifetime is 1 year.

Contact

Address: 19 Rue du Mercure, ZI Ben Arous

2013 Ben Arous - Tunisia. Tel: +216 71 383 675 Fax: +216 71 383 716

Email: commercial@hosta-polymers.com

Ed. 01 30/03/2015